
COSWICK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1192-4215

COSWICK
Solid Hardwood Floors






COLLECTION | PARQUETRY
COLOR | CHAMBORD
Wood species | Oak
Grade | Tavern
Pattern | Pyramid
Constructions | 3-layer G&G Engineered Flooring
Size | 19,05 x 190 x 440 mm (¾" x 7 ½" x 17 ⅜")
Finish | Silk Oil

CONSTRUCTION : 3-LAYER G&G ENGINEERED FLOORING

DIMENSIONS :	
Thickness	19,05 mm (¾")
Width	190 mm (7 ½)
Length	440 mm (17 ⅜")
Average length	-
Microbevel	0,5 mm
Joint type	groove and groove (G&G)



PACKAGING :	BOX	PALLET
Content:	1,257m²	40 (50,28 m²)
Weight	16 kg	653 kg
H x W x L	194 x 396 x 468 mm	1097 x 800 x1880 mm
Content:	13,53 sq.ft.	541,2 sq.ft.
Weight	35 lb	1446 lb
H x W x L	8" x 16" x 18"	43" x 31" x 74"

DEVIATIONS :		
Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3 СТБ 2121
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	
Cup	≤ 0,2 % of plank width	
Bow	≤ 0,1 % of length	EN 13489
Spring	≤ 0,5 % of length	

CHARACTERISTICS :		
Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,118 m²·K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK OIL

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Silk matte 9-18 GU/85°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS :		
Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk Oil finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : TAVERN

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	No limit	Bark pocket	No limit (after filling)
Colour variation	No limit	Pith	Permitted
Knot	No limit (after filling)	Slope of grain	Permitted
Checks	Permitted filled up to 3 mm in width	Medullary ray	Permitted

Coswick Ltd.
2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

nwfa National Wood Flooring Association
ECO FRIENDLY
No added formaldehyde
ISO 9001
FSC
CE